

SCHEDA TECNICA PRODOTTO

Safety navy

| Subject | Result | Test method |
|--|-----------------|-----------------|
| Back carrier | 0.52mm PVC | Caliper method |
| Type of adhesive | Solvent acrylic | N/A |
| Adhesive thickness | 0.06mm | Caliper method |
| Overall thickness | 0.58mm | Caliper method |
| Initial tack (kg/25.4mm ²) | 0.67 | PSTC-I6 |
| Peel strength (kg/25.4mm ²) | 0.80 | PSTC-I |
| Tear resistance (g) | 5600 +/- 200 | PSTC-39 |
| Temperature range | -30°C to +70°C | See notes below |
| Maximum size of production roll | 1194mmx100m | N/A |

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

Coefficient of friction data

| | Dry surface test result | Wet surface test result |
|-------------|-------------------------|-------------------------|
| Safety navy | 106 4S | 42 4S |

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.



INVESTOR IN PEOPLE